

LEVEL 5

- Achieves a Level 5 finish in lieu of a skim coat as described in the Gypsum Associations "The Levels of Gypsum Board Finish" GA-214/ASTM C-840
- Single coat application
- Low VOC "Environmentally Friendly"
- Dries White

DIRECTIONS

BLOCK, PLASTER and CONCRETE

Substrate must be clean and free of dust, efflorescence and mildew. Block, hard plaster and concrete must be inside and covered. Concrete will need to age minimum of 60 days before treatment commences. All surfaces need to be thoroughly dry before the product is applied.

Remove contaminants such as oil and/or any other foreign matters likely to prevent maximum adhesion. All tool marks, nicks and surface defects will require remedial attention prior to the application of LEVEL 5.

NEW DRYWALL

Treat all joints, fasteners and accessories to achieve a Level 4 application. Pay additional attention to metal trims with large exposed surfaces. Refer to GA 214 "Recommended Levels of Gypsum Board Finish" or ASTM C-840.

JOB CONDITIONS

A minimum temperature of 55°F (12.7° C) to be maintained 48 hours prior through application and until dry and stable.

MIXING

Mix by stirring. Power mixing is not recommended.

EQUIPMENT

Airless application (1.0 GPM) is recommended. Tip size of .019" to .031". Air pressure range 2600 to 3200 psi.

COVERAGE

Approximately 100 to 130 sq ft per gallon when applied at 15-20 mils WFT (10-15 mils DFT). Actual coverage may vary depending on drywall surface, spraying techniques, coating uniformity and thickness.

DRYING TIME

Touch dry in approximately 40-90 min under normal drying conditions. Drying times may be altered with changes in ambient temps, excessive humidity.

CLEAN-UP

LEVEL 5 is water-soluble: clean up with water.

Submittal / Approval	
Signature	Stamp